



Product Specifications for INVISI-lock™

Flexible magnetic sheeting. Available in 24" & 40" width rolls and custom sheets

Property		Unit of Measure	Typical Value	Test Method
Thickness	(surface)	mils		Micro-gauge
		mils	15	
		mils	20	
		mils	30	
Approved Invisilock™ magnet for the Visual Magnetics™ Graphic System				
Thickness	(surface)	mils		
	(adhesive)	mils	1.8	
Approved magnet for the Visual Magnetics™ ACTIVEwall™ (magnetized 2-sides)				
Thickness	(surface)	mils		
		mils	40	
Tensile Strength		psi	700↑	ASTM D 882
		kg/cm ²	49	
Surface hardness		durometer	D60	
Specific Gravity			3.5	
Shrinkage		%	<1.5	ASTM D 2578
		° Fahrenheit	158	
Face color		Available in plain, white face and adhesive-backed		

The above data is based on research, testing and industry experience, but does not constitute a warranty. Additional end-user testing is necessary for ALL materials, but most importantly adhesive-backed magnet.

Variables to consider but not limited to ensure proper adhesion success are: 1) surface type and texture 2) surface finish, including paints and primers used 3) surface preparation 4) surface environment conditions including extreme temperature shifts 5) Magnet must be to room temperature when applying.